



## Ter wax HG Microcrystalline Wax

Characteristics	Specification
Congealing Point	77 °C – 83 °C
Color	0.5 (ASTM 1500)
Penetration	9 – 15 (x 0.1 mm) at 25 °C
Viscosity	12 - 17 mPa.s at 100 °C
Drop Point	80 °C – 86 °C
U.S. Food & Drug Administration	Paragraph 172.886, 175.105, 176.170 176.180, 178.371



Microcrystalline waxes consist of odorless, tasteless, non-polar hydrocarbons with relatively high melting points.

Microcrystalline waxes act as bases for chewing gum, lipstick, cold creams and ointments. Other uses include wax impregnated paper, film, foil, and corrugated board for food packaging. Other products such as crayons, candles and caulk to sealants and fine polishes start with microcrystalline wax.

Packaging: Pastilles in a 25 kg plastic bag