



## Ter wax HH Microcrystalline Wax

Characteristics	Specification
Congealing Point	70 °C – 76 °C
Color	Off white to yellow
Penetration	20 – 30 (x 0.1 mm) at 25 °C
Viscosity	9 – 15 mPa.s at 100 °C
Drop Point	75 °C – 80 °C



Microcrystalline waxes consist of odorless, tasteless, non-polar hydrocarbons with relatively high melting points.

Microcrystalline waxes act as bases for chewing gum, lipstick, cold creams and ointments. Other uses include wax impregnated paper, film, foil, and corrugated board for food packaging. Other products such as crayons, candles and caulk to sealants and fine polishes start with microcrystalline wax.

Packaging: Slabs in a 25 kg carton