



Ter wax LMP Microcrystalline Wax

Characteristics	Specification
Congealing Point	62 °C – 66 °C
Color	1.5 max. (Lovibond 6" cell)
Penetration	70 - 160 (x 0.1 mm) at 43 °C
Penetration	20 – 30 (x 0.1 mm) at 25 °C
Oil Content	1 % m/m max.
U.S. Food & Drum Administration	Paragraph 172.886, 178.371



Microcrystalline waxes consist of odorless, tasteless, non-polar hydrocarbons with relatively high melting points.

Microcrystalline waxes act as bases for chewing gum, lipstick, cold creams and ointments. Other uses include wax impregnated paper, film, foil, and corrugated board for food packaging. Other products such as crayons, candles and caulk to sealants and fine polishes start with microcrystalline wax.

Packaging: Slabs in a 25 kg carton