



Ter wax P 1700
Non-oxidized Polyethylene wax

Characteristics	Specification
Density	.93 - .95 (g/cm ³) at 20 °C
Drop Point	110 °C – 115 °C
Solidification Point	100 °C – 105 °C
Penetration	Max. 1 (mm x 10 ²)
Viscosity	100 – 200 (mm ² /s) at 140 °C
Average Molecular Weight	1700

GEHRING-MONTGOMERY, INC.



Low molecular weight polyethylenes having wax like properties are made either by high-pressure polymerization or low pressure (Zeigler-type catalysts) polymerization.

These waxes are mainly used in plastics processing, paraffin compounds, printing inks, lacquers, car products and hot melt adhesives.

Packaging: 25 kg plastic bag

Distributed by Gehring-Montgomery, Inc.

710 Louis Drive
Warminster, USA, PA 18974
Phone: 215/957-1234
Fax: 215/957-1311
chemicals@gehring-montgomery.com